



PRIMER 001



TM PRIMER 001

TM PRIMER 001 is a primer mainly intended for priming concrete, light-weight concrete, HDF, chip-board, plasterboard, etc.

TM PRIMER 001 can be covered when dry – after approx. 1-10 hours. However, it should not be older than three days.



- Acrylic primer
- Small particle size
- Good adhesion
- Alkali resistant
- All substrates

TM PRIMER 001

General

TM PRIMER 001 is a primer intended for priming concrete, light-weight concrete, wood, chipboard, sheet plastics, clinkers, etc.

TM PRIMER 001 can be covered when dry, normally after 1-10 hours. It should not be more than three days old when filling is carried out.

Presentation

TM PRIMER 001 is supplied in 1,5 and 25 kg plastic containers.

Method description

Preparation

Surfaces to be primed must be firm and clean. Cement skin, colorants, grease, porous and loose contaminants

must be removed. The floor should be vacuumed carefully.

Application

For an absorbent substrate TM PRIMER 001 should be thinned with three parts water. With highly absorbent surfaces and at high temperatures, floors should be treated with 1:3 twice. Do this after the first coat has formed a film.

Mix the water and primer thoroughly and then brush on.

With a non-absorbent substrate, e.g. chipboard etc., prime the floor with part filler and part concentrated primer. Mix the compound for 30 seconds and then brush on.

TECHNICAL DATA

Moisture content %	45	Alkali resistant	Yes
Storage temperature not below	+10°C	FLEC emissions tested	Yes
Coverable (hours)	1-10	Meets Hus AMA	Yes
Shelf life	6	Coverage litre/m ²	Ca. 0,10-0,15 h



TM Progress AB

Head Office

TM Progress AB
Kavelvägen 7, Box 395
SE-891 28 Örnsköldsvik
Tel +46 (0)660 29 95 30
Fax +46 (0)660 37 67 65
E-mail: info@tmprogress.se
Internet: www.tmprogress.se

Sales

Örnsköldsvik +46 (0)70 699 74 70
Stockholm +46 (0)70 688 44 30
Stockholm +46 (0)70 699 91 00
Stockholm +46 (0)70 609 95 30
Örebro +46 (0)70 552 23 72
Göteborg +46 (0)70 325 85 40
Växjö +46 (0)70 892 32 22
Osby +46 (0)70- 860 99 09

Orders & Delivery

TM Progress AB
Olbergavägen 8
SE-734 92 Hallstahammar
Tel +46 (0)220 105 10
Fax +46 (0)220 169 60

